



TAREX TURBO UHPD 10W-40

SYNTHETIC MOTOR OIL - CJ-4/SN

Product Description:

TAREX TURBO UHPD 10W-40 Synthetic Motor Oil is a low ash advance synthetic heavy duty diesel engine oil that helps to extend engine life in the most severe operating conditions. The oil is formulated using synthetic technology and the highest quality base oils to deliver excellent performance in both new and older engines. It meets the long life requirements of major engine manufacturers and gives protection over a long time period. TAREX TURBO UHPD 10W-40 Synthetic Motor Oil CJ-4/SN provides lubrication to modern, high performance, low emissions engines used in severe applications.

Applications:

Suitable for heavy duty fleets working under severe conditions. Suitable for extended oil drain intervals in heavy duty trucks, buses and off road machinery where API CJ-4/SN performance level with diesel particulate filters is recommended.

Benefits:

- ❖ Outstanding protection against oil thickening, high temperature deposits, sludge build up and, oil degradation
- ❖ Excellent anti-wear, anti-scuff properties with bore polishing and corrosion protection
- ❖ Helps to improve oil circulation
- ❖ Stay-in grade shear stability with low volatility
- ❖ Helps to maintain engine efficiency, long engine life and long oil life
- ❖ Helps to improve corrosion protection and extend oil drain intervals

Meets the Performances:

API CJ-4/SN; ACEA E6/E9/E7; MB 228.31/228.51; MAN M3477/3271/3677; Volvo VDS-4/VDS-3/CNG; Renault Truck RXD/RLD/RLD-2/RLD-3; Mack EO-M Plus/EO-N/EO-O; JASO DH-2, CAT ECF-3; Cummins CES 20081; Scania LDF-3

Please check your owner's manual for the manufacturer's recommended oil viscosity grade and API classification and approvals.

Technical Data:

TAREX	Test method	
API		CJ-4/SN
SAE Grade		10W-40
Density at 15°C gr/cm ³	ASTM D 1298	0.86-0.87
Viscosity at 40°C cSt	ASTM D 445	95-100
Viscosity at 100°C cSt	ASTM D 445	14.3-14.7
CCS Viscosity at -25°C, mPa.s	ASTM D 5293	Max. 7000
Viscosity Index	ASTM D 2270	156
Flash point °C	ASTM D 92	Min. 220
Pour point °C	ASTM D 97	-41
Total Base Number mg KOH/g	ASTM D 2896	9.5-10
Sulphated Ash, %	ASTM D 874	0.88

Above values are the typical values of the products and may vary with each batch