



TAREX Blu 5W-20 SN

FULL SYNTHETIC MOTOR OIL – SN/GF-5

Product Description:

TAREX Blu 5W-20 Full Synthetic Motor Oil – SN/GF-5 is a full synthetic engine oil formulated with high-quality synthetic base oils. It delivers high levels of fuel economy combined with enhanced wear protection, even under the most demanding operating conditions. The unique combination of high-quality synthetic base oils and performance additive components enables high-performance engines to achieve maximum levels of efficiency, torque, and horsepower while extending engine durability by minimizing wear and keeping the engine virtually free of harmful deposits.

Applications:

TAREX Blu 5W-20 Full Synthetic Motor Oil – SN/GF-5 is recommended for turbocharged and high-powered passenger cars, trucks, sport utility vehicles, and other mobile or stationary engines.

Benefits:

- ❖ Provides improved fuel economy
- ❖ Reduces friction to maximize horsepower
- ❖ Excellent protection against the formation of sludge and harmful deposits
- ❖ Superior lubrication flow and pumpability at high and low temperatures
- ❖ Lower pour point reduces start-up wear during cold weather and provides superb cold-start protection
- ❖ High resistance to oxidation keeps the oil fresher for longer
- ❖ Outstanding wear protection for vehicles of all ages, lowering maintenance costs by keeping the engine clean and improving performance

Meets the Specifications:

API SN/Resource Conserving; ACEA A1/B1/C2/C5; ILSAC GF-5; MB 229.31/229.51/229.52; Dexos 2®; GM 6094M; VW 502.00/505.01/504.00; Ford WSS M2C948-B/M2C930-A/M2C946-A/M2C945-A/M2C929-A; Honda HTO-06; Chrysler 6395

Please check your owner's manual for the manufacturer's recommended oil viscosity grade and API classification and approvals

Technical Data:

TAREX	Test Method	
API		SN/GF-5
SAE Grade		5W-20
Density at 15 °C, gr/cm ³	ASTM D 1298	0.84 - 0.85
Viscosity at 40 °C, cSt	ASTM D 445	47 - 52
Viscosity at 100 °C, cSt	ASTM D 445	8.7 - 9.2
CCS Viscosity at -30 °C, mPa.s	ASTM D 5293	Max. 6600
Viscosity Index	ASTM D 2270	165
Flash Point, °C	ASTM D 92	225
Pour Point, °C	ASTM D 97	-42
Total Base Number, mg KOH/g	ASTM D 2896	7.6 – 8.0
Sulphated Ash, %	ASTM D 874	0.81

Above values are the typical values of the products and may vary with each batch.